

# Laykold® Masters Wearcoat

## 2K-PUR Coating

is a solvent-free, 2-component, polyurethane based coating.

### Product specifications

<b>Density</b>	@ 23 °C	1.09 g/cm <sup>3</sup>
<b>Viscosity</b>	@ 23 °C	1702 mPas
<b>Mixing ratio</b>	Part A : Part B (by weight)	2.9 : 1
<b>Pot life</b>	@ 23 °C; 50 % relative humidity	40–60 minutes
<b>Touch dry</b>	@ 23 °C; 50 % relative humidity	8 hours
<b>Subsequent coating</b>	@ 23 °C; 50 % relative humidity	8–24 hours
<b>Full cure</b>	@ 23 °C; 50 % relative humidity	72 hours
<b>Processing temperature</b>		mind. 10 °C – 30 °C (3 °C above dew point)

### Processing specifications

Mix the two components of Laykold Wearcoat by adding the B component to the A component and mixing for a minimum of three minutes. The material should then be poured into a separate clean container and mixed for a further 3 minutes.

Apply the Laykold Wearcoat to the substrate using a squeegee.

### Safety warnings

Never use Laykold Wearcoat near flames or open light. Smoking is also strictly prohibited during the application process. Wear approved eye protection and gloves during application. Adequate ventilation or use of a respirator is required in enclosed spaces.

### Packaging

Part A: 13 kg pail

Part B: 4.5 kg pail

### Storage

Store Laykold Wearcoat in a dry and cool place but not below 10 °C. Shelf life of product stored in original unopened containers is 24 months.